AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) | Date: 26-12-2020

Name of Work : Comprehensive Development works in ward No. 03 Attur

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	B.B Umesh (S.M.L.P Asphats)
Customer Reference	EE(PROJECT)/YNK ZONE/WO/173/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	19-12-2020
Sample Type	C.C Road Top Layer
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M30/ 7 Days Compressive Strength
Date of Test	26-12-2020
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Weight of the sample	Failure Load	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	kg	KN	N/mm²	N/mm²
1	C.C Road	M30	19-12-2020	26-12-2020	150x150x150	22500	8.7	456	20.3	20.51
2	C.C Road	M30	19-12-2020	26-12-2020	150x150x150	22500	8.8	466	20.7	
3	C.C Road	M30	19-12-2020	26-12-2020	150x150x150	22500	8.9	463	20.6	

Remarks :

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

AARTN ASSOCIATES * BANGALORE *

Scanned by TapScanner

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) | Date: 26-12-2020

Name of Work : Comprehensive Development works in ward No. 03 Attur

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	B.B Umesh (S.M.L.P Asphats)
Customer Reference	EE(PROJECT)/YNK ZONE/WO/173/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	19-12-2020
Sample Type	C.C Road Top Layer
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M30/ 7 Days Compressive Strength
Date of Test	26-12-2020
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Weight of the sample	Failure Load	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	kg	KN	N/mm^2	N/mm^2
1	C.C Road	M30	19-12-2020	26-12-2020	150x150x150	22500	8.82	470	20.9	21.06
2	C.C Road	M30	19-12-2020	26-12-2020	150x150x150	22500	8.97	480	21.3	
3	C.C Road	M30	19-12-2020	26-12-2020	150x150x150	22500	9.03	473	21.0	

Remarks :

AARTN ASSOCIATES BANGALORE

Scanned by TapScanner

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) | Date: 26-12-2021

Name of Work : Comprehensive Development works in ward No. 03 Attur

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	B.B Umesh (S.M.L.P Asphats)
Customer Reference	EE(PROJECT)/YNK ZONE/WO/173/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	19-12-2020
Sample Type	C.C Road Top Layer
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M30/ 7 Days Compressive Strength
Date of Test	26-12-2020
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Weight of the sample	Failure Load	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	kg	KN	N/mm^2	N/mm^2
1	C.C Road	M30	19-12-2020	26-12-2020	150x150x150	22500	8.25	460	20.5	20.57
2	C.C Road	M30	19-12-2020	26-12-2020	150x150x150	22500	8.40	471	20.9	
3	C.C Road	M30	19-12-2020	26-12-2020	150x150x150	22500	8.46	457	20.3	

Remarks :

AARTN ASSOCIATES BANGALORE

Scanned by TapScanner

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) — Date: 05-01-2021

Name of Work : Comprehensive Development works in ward No. 03 Attur

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	B.B Umesh (S.M.L.P Asphats)
Customer Reference	EE(PROJECT)/YNK ZONE/WO/173/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	29-12-2020
Sample Type	C.C Road Top Layer
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M30/ 7 Days Compressive Strength
Date of Test	05-01-2021
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Weight of the sample	Failure Load	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	kg	KN	N/mm^2	N/mm^2
1	C.C Road	M30	29-12-2020	05-01-2021	150x150x150	22500	8.52	450	20.0	20.00
2	C.C Road	M30	29-12-2020	05-01-2021	150x150x150	22500	8.3	448	19.9	
3	C.C Road	M30	29-12-2020	05-01-2021	150x150x150	22500	8.64	453	20.1	

Remarks :

AARTN ASSOCIATES BANGALORE

Scanned by TapScanner

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) — Date: 05-01-2021

Name of Work : Comprehensive Development works in ward No. 03 Attur

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	B.B Umesh (S.M.L.P Asphats)
Customer Reference	EE(PROJECT)/YNK ZONE/WO/173/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	29-12-2020
Sample Type	C.C Road Top Layer
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M30/ 7 Days Compressive Strength
Date of Test	05-01-2021
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Weight of the sample	Failure Load	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	kg	KN	N/mm^2	N/mm^2
1	C.C Road	M30	29-12-2020	05-01-2021	150x150x150	22500	8.62	458	20.4	20.36
2	C.C Road	M30	29-12-2020	05-01-2021	150x150x150	22500	8.4	456	20.3	
3	C.C Road	M30	29-12-2020	05-01-2021	150x150x150	22500	8.74	461	20.5	

Remarks :

AARTN ASSOCIATES

Scanned by TapScanner

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) — Date: 05-01-2021

Name of Work : Comprehensive Development works in ward No. 03 Attur

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	B.B Umesh (S.M.L.P Asphats)
Customer Reference	EE(PROJECT)/YNK ZONE/WO/173/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	29-12-2020
Sample Type	C.C Road Top Layer
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M30/ 7 Days Compressive Strength
Date of Test	05-01-2021
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Weight of the sample	Failure Load	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	kg	KN	N/mm^2	N/mm^2
1	C.C Road	M30	29-12-2020	05-01-2021	150x150x150	22500	8.53	451	20.0	20.05
2	C.C Road	M30	29-12-2020	05-01-2021	150x150x150	22500	8.31	449	19.9	
3	C.C Road	M30	29-12-2020	05-01-2021	150x150x150	22500	8.65	454	20.2	

Remarks :

JC

AARTN ASSOCIATES BANGALORE

Scanned by TapScanner

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8046505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5)

Date: 06-01-2021

Name of Work : Comprehensive Development works in ward No. 03 Attur

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	B.B Umesh (S.M.L.P Asphalts)
Customer Reference	EE/PROJECT)/YNK ZONE/WO/173/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	29-12-2020
Sample Type	C.C Road Top Layer
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M30/ 7 Days Compressive Strength
Date of Test	05-01-2021
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Weight of the sample	Failure Load	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	kg	KN	N/mm^2	N/mm^2
1	C.C Road	M30	29-12-2020	05-01-2021	150x150x150	22500	8.51	450	20.0	20.00
2	C.C Road	M30	29-12-2020	05-01-2021	150x150x150	22500	8.29	448	19.9	
3	C.C Road	M30	29-12-2020	05-01-2021	150x150x150	22500	8.63	453	20.1	

Remarks :

JE

Scanned by TapScanner

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8088505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5)

Date: 05-01-2021

Name of Work : Comprehensive Development works in ward No. 03 Attur

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	B.B Umesh (S.M.L.P Asphalts)
Customer Reference	EE/PROJECT)/YNK ZONE/WO/173/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	29-12-2020
Sample Type	C.C Road Top Layer
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M30/ 7 Days Compressive Strength
Date of Test	05-01-2021
Location	

Sl. No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Weight of the sample	Failure Load	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	kg	KN	N/mm²	N/mm²
	C.C Road	M30	29-12-2020	05-01-2021	150x150x150	22500	8.48	450	20.0	20.00
	C.C Road	M30	29-12-2020	05-01-2021	150x150x150	22500	8.26	448	19.9	
	C.C Road	M30	29-12-2020	05-01-2021	150x150x150	22500	8.6	453	20.1	

Remarks :

AARTN ASSOCIATES BANGALORE

Scanned by TapScanner

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) — Date: 12-01-2021

Name of Work : Comprehensive Development works in ward No. 03 Attur

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	B.B Umesh (S.M.L.P Asphats)
Customer Reference	EE(PROJECT)/YNK ZONE/WO/173/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	05-01-2021
Sample Type	C.C Road Top Layer
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M30/ 7 Days Compressive Strength
Date of Test	12-01-2021
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Weight of the sample	Failure Load	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	kg	KN	N/mm^2	N/mm^2
1	C.C Road	M30	05-01-2021	12-01-2021	150x150x150	22500	8.56	463	20.6	20.93
2	C.C Road	M30	05-01-2021	12-01-2021	150x150x150	22500	8.79	481	21.4	
3	C.C Road	M30	05-01-2021	12-01-2021	150x150x150	22500	8.62	469	20.8	

Remarks :

Scanned by TapScanner

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5)

Date: 12-01-2021

Name of Work : Comprehensive Development works in ward No. 03 Attur

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	B.B Umesh (S.M.L.P Asphats)
Customer Reference	EE(PROJECT)/YNK ZONE/WO/173/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	05-01-2021
Sample Type	C.C Road Top Layer
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M30/ 7 Days Compressive Strength
Date of Test	12-01-2021
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Weight of the sample	Failure Load	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	kg	KN	N/mm^2	N/mm^2
1	C.C Road	M30	05-01-2021	12-01-2021	150x150x150	22500	8.62	468	20.8	20.80
2	C.C Road	M30	05-01-2021	12-01-2021	150x150x150	22500	8.4	466	20.7	
3	C.C Road	M30	05-01-2021	12-01-2021	150x150x150	22500	8.74	471	20.9	

Remarks :

JE

Scanned by TapScanner

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) — Date: 12-01-2021

Name of Work : Comprehensive Development works in ward No. 03 Attur

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	B.B Umesh (S.M.L.P Asphats)
Customer Reference	EE(PROJECT)/YNK ZONE/WO/173/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	05-01-2021
Sample Type	C.C Road Top Layer
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M30/ 7 Days Compressive Strength
Date of Test	12-01-2021
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Weight of the sample	Failure Load	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	kg	KN	N/mm^2	N/mm^2
1	C.C Road	M30	05-01-2021	12-01-2021	150x150x150	22500	8.67	471	20.9	20.94
2	C.C Road	M30	05-01-2021	12-01-2021	150x150x150	22500	8.45	469	20.8	
3	C.C Road	M30	05-01-2021	12-01-2021	150x150x150	22500	8.79	474	21.0	

Remarks :

Scanned by TapScanner

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) | Date: 12-01-2021

Name of Work : Comprehensive Development works in ward No. 03 Attur

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	B.B Umesh (S.M.L.P Asphats)
Customer Reference	EE(PROJECT)/YNK ZONE/WO/173/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	05-01-2021
Sample Type	C.C Road Top Layer
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M30/ 7 Days Compressive Strength
Date of Test	12-01-2021
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Weight of the sample	Failure Load	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	kg	KN	N/mm^2	N/mm^2
1	C.C Road	M30	05-01-2021	12-01-2021	150x150x150	22500	8.71	463	20.6	20.58
2	C.C Road	M30	05-01-2021	12-01-2021	150x150x150	22500	8.49	461	20.5	
3	C.C Road	M30	05-01-2021	12-01-2021	150x150x150	22500	8.83	466	20.7	

Remarks :

Scanned by TapScanner

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5)

Date: 12-01-2021

Name of Work : Comprehensive Development works in ward No. 03 Attur

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	B.B Umesh (S.M.L.P Asphats)
Customer Reference	EE(PROJECT)/YNK ZONE/WO/173/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	05-01-2021
Sample Type	C.C Road Top Layer
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M30/ 7 Days Compressive Strength
Date of Test	12-01-2020
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Weight of the sample	Failure Load	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	kg	KN	N/mm^2	N/mm^2
1	C.C Road	M30	05-01-2021	12-01-2020	150x150x150	22500	8.62	460	20.4	20.45
2	C.C Road	M30	05-01-2021	12-01-2020	150x150x150	22500	8.4	458	20.3	
3	C.C Road	M30	05-01-2021	12-01-2020	150x150x150	22500	8.74	463	20.6	

Remarks :

AARTN ASSOCIATES BANGALORE

Scanned by TapScanner

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) | Date: 12-01-2021

Name of Work : Comprehensive Development works in ward No. 03 Attur

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	B.B Umesh (S.M.L.P Asphats)
Customer Reference	EE(PROJECT)/YNK ZONE/WO/173/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	05-01-2021
Sample Type	C.C Road Top Layer
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M30/ 7 Days Compressive Strength
Date of Test	12-01-2021
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Weight of the sample	Failure Load	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	kg	KN	N/mm^2	N/mm^2
1	C.C Road	M30	05-01-2021	12-01-2021	150x150x150	22500	8.57	458	20.4	20.36
2	C.C Road	M30	05-01-2021	12-01-2021	150x150x150	22500	8.35	456	20.3	
3	C.C Road	M30	05-01-2021	12-01-2021	150x150x150	22500	8.69	461	20.5	

Remarks :

AARTN ASSOCIATES BANGALORE

Scanned by TapScanner

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) — Date: 18-01-2021

Name of Work : Comprehensive Development works in ward No. 03 Attur

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	B.B Umesh (S.M.L.P Asphats)
Customer Reference	EE(PROJECT)/YNK ZONE/WO/173/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	11-01-2021
Sample Type	C.C Road Top Layer
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M30/ 7 Days Compressive Strength
Date of Test	18-01-2021
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Weight of the sample	Failure Load	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	kg	KN	N/mm^2	N/mm^2
1	C.C Road	M30	11-01-2021	18-01-2021	150x150x150	22500	8.52	452	20.1	20.09
2	C.C Road	M30	11-01-2021	18-01-2021	150x150x150	22500	8.3	450	20.0	
3	C.C Road	M30	11-01-2021	18-01-2021	150x150x150	22500	8.64	455	20.2	

Remarks :

JE

AARTN ASSOCIATES BANGALORE

Scanned by TapScanner

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) — Date: 18-01-2021

Name of Work : Comprehensive Development works in ward No. 03 Attur

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	B.B Umesh (S.M.L.P Asphats)
Customer Reference	EE(PROJECT)/YNK ZONE/WO/173/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	11-01-2021
Sample Type	C.C Road Top Layer
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M30/ 7 Days Compressive Strength
Date of Test	18-01-2021
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Weight of the sample	Failure Load	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	kg	KN	N/mm^2	N/mm^2
1	C.C Road	M30	11-01-2021	18-01-2021	150x150x150	22500	8.52	456	20.3	20.27
2	C.C Road	M30	11-01-2021	18-01-2021	150x150x150	22500	8.3	454	20.2	
3	C.C Road	M30	11-01-2021	18-01-2021	150x150x150	22500	8.64	459	20.4	

Remarks :

BANGALORE ★ AARTN ASSOCIATES ★

Scanned by TapScanner

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) — Date: 18-01-2021

Name of Work : Comprehensive Development works in ward No. 03 Attur

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	B.B Umesh (S.M.L.P Asphats)
Customer Reference	EE(PROJECT)/YNK ZONE/WO/173/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	11-01-2021
Sample Type	C.C Road Top Layer
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M30/ 7 Days Compressive Strength
Date of Test	18-01-2021
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Weight of the sample	Failure Load	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	kg	KN	N/mm^2	N/mm^2
1	C.C Road	M30	11-01-2021	18-01-2021	150x150x150	22500	8.48	452	20.1	20.09
2	C.C Road	M30	11-01-2021	18-01-2021	150x150x150	22500	8.26	450	20.0	
3	C.C Road	M30	11-01-2021	18-01-2021	150x150x150	22500	8.6	455	20.2	

Remarks :

AARTN ASSOCIATES BANGALORE

Scanned by TapScanner

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5)

Date: 18-01-2021

Name of Work : Comprehensive Development works in ward No. 03 Attur

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	B.B Umesh (S.M.L.P Asphats)
Customer Reference	EE(PROJECT)/YNK ZONE/WO/173/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	11-01-2021
Sample Type	C.C Road Top Layer
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M30/ 7 Days Compressive Strength
Date of Test	18-01-2021
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Weight of the sample	Failure Load	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	kg	KN	N/mm^2	N/mm^2
1	C.C Road	M30	11-01-2021	18-01-2021	150x150x150	22500	8.28	455	20.2	20.23
2	C.C Road	M30	11-01-2021	18-01-2021	150x150x150	22500	8.06	453	20.1	
3	C.C Road	M30	11-01-2021	18-01-2021	150x150x150	22500	8.4	458	20.3	

Remarks :

AARTN ASSOCIATES ★ DATE ★ BANGALORE

Scanned by TapScanner

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

Date: 18-01-2021

IS: 516-1959 (Method of tests for strength of Concrete C1.5)

Name of Work : Comprehensive Development works in ward No. 03 Attur

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	B.B Umesh (S.M.L.P Asphats)
Customer Reference	EE(PROJECT)/YNK ZONE/WO/173/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	11-01-2021
Sample Type	C.C Road Top Layer
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M30/ 7 Days Compressive Strength
Date of Test	18-01-2021
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Weight of the sample	Failure Load	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	kg	KN	N/mm^2	N/mm^2
1	C.C Road	M30	11-01-2021	18-01-2021	150x150x150	22500	8.16	452	20.1	20.09
2	C.C Road	M30	11-01-2021	18-01-2021	150x150x150	22500	7.94	450	20.0	
3	C.C Road	M30	11-01-2021	18-01-2021	150x150x150	22500	8.28	455	20.2	

Remarks :

AARTN ASSOCIATES BANGALORE

Scanned by TapScanner

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5)

Date: 18-01-2021

Name of Work : Comprehensive Development works in ward No. 03 Attur

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	B.B Umesh (S.M.L.P Asphats)
Customer Reference	EE(PROJECT)/YNK ZONE/WO/173/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	11-01-2021
Sample Type	C.C Road Top Layer
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M30/ 7 Days Compressive Strength
Date of Test	18-01-2021
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Weight of the sample	Failure Load	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	kg	KN	N/mm^2	N/mm^2
1	C.C Road	M30	11-01-2021	18-01-2021	150x150x150	22500	8.19	457	20.3	20.32
2	C.C Road	M30	11-01-2021	18-01-2021	150x150x150	22500	7.97	455	20.2	
3	C.C Road	M30	11-01-2021	18-01-2021	150x150x150	22500	8.31	460	20.4	

Remarks :

AARTN ASSOCIATES DATE BANGALORE

Scanned by TapScanner